



TECHNICAL DATA SHEET

TDS 085

Revision:	Date:	Page:
06	06/27/18	1/1

RESIDHERE TE 25 H

Modified rosin and glycol derivatives-based resin.

VERIFICATIONS

Characteristics	UN	Specification / Tolerance	Method
Color Gardner	-	4 max.	ML SC 006
Acid Number	mgKOH/g	20 min.	ML SC 001
Viscosity (50 °C)	mPa.s	1500 – 5500	ML SC 028
Hydroperoxide Index	mEq/Kg	10 max.	ML SC 031
Solubility	-	-	-
* Acetates	-	Soluble	ML SC 012
* Alcohols	-	Insoluble	ML SC 012
* Aromatic Hydrocarbons	-	Soluble	ML SC 012
* Aliphatic Hydrocarbons	-	Soluble	ML SC 012
* Drying oil	-	Soluble	ML SC 012

* The sporadic analyzed parameters above do not characterize the product and should be taken only as reference.

APPLICATIONS

- Hot-melt, PSA, glues and adhesives in general;
- Depilatory waxes;
- Tapes and adhesive papers.

BENEFITS

- Excellent tack;
- Higher plasticity.

PACKAGING

Type	Size	Shelf life
Steel drums	180 Kg	12 months

DISCLAIMER

To prevent accidents and environmental impacts, please check the product SDS.



We request our customers to test our products before using them on industrial scale. The user of our products bears the responsibility of determining their suitability for a particular application or formulation or determining that the products or their use do not infringe any intellectual property. We do not assume any responsibility or warranty, expressed or implied, resulting from handling, usage and storage whether performed according to the instructions contained in this document, whether used alone or in combination with other products. The buyer assumes all responsibility and liability for loss or damage arising from the handling and use of our products, either alone or in combination with other products.

Elaborated: Murilo M. Quarcioni

Revised: Rafaela Silva

Approved: Alexandre Tresmondi