

	TECHNICAL DATA SHEET	TDS 250		
		Revision:	Date:	Page:
		01	02/07/2022	1/1

RESIDHERE AM 125 S

Gum rosin modified with maleic anhydride.

VERIFICATIONS			
Characteristics	UN	Specification / Tolerance	Method
Color Gardner	-	10 max.	ML SC 006
Acid Number	mgKOH/g	40 max.	ML SC 001
Viscosity Ford Cup (50% w/w in Toluene) (25 °C)	-	15 – 20	ML SC 061
Softening Point (Ring and Ball)	°C	125 – 135	ML SC 002
Solubility	-	-	-
* Acetates	-	Soluble	ML SC 012
* Alcohols	-	Insoluble	ML SC 012
* Aliphatic Hydrocarbons	-	Soluble	ML SC 012
* Aromatic Hydrocarbons	-	Soluble	ML SC 012
* Drying oil	-	Soluble	ML SC 012

* The sporadic analyzed parameters above do not characterize the product and should be taken only as reference.

APPLICATIONS

- Lacquers, sealants and varnishes based on Nitrocellulose;
- Synthetic enamel and paints for road demarcation.

BENEFITS

- Promotes high gloss, fast drying and good hardness;
- Improve wetting and adhesion.

PACKAGING

Type	Size	Shelf life
Flakes Paper bags	25 Kg	12 months

DISCLAIMER

To prevent accidents and environmental impacts, please check the product SDS.



We request our customers to test our products before using them on industrial scale. The user of our products bears the responsibility of determining their suitability for a particular application or formulation or determining that the products or their use do not infringe any intellectual property. We do not assume any responsibility or warranty, expressed or implied, resulting from handling, usage and storage whether performed according to the instructions contained in this document, whether used alone or in combination with other products. The buyer assumes all responsibility and liability for loss or damage arising from the handling and use of our products, either alone or in combination with other products.

Elaborated: Allan Ribeiro	Revised: Rafaela Silva / Sérgio Ribeiro	Approved: Sérgio Ribeiro
----------------------------------	---	---------------------------------