

## **TECHNICAL DATA SHEET**

TDS 012				
Revision:	Date:	Page:		
02	2024-06-21	1/1		

## **RESIDHERE DV 125 SM**

Modified rosin ester.

VERIFICATIONS						
Characteristics	UN	Specification / Tolerance	Method			
Color Gardner	-	7 max.	ML SC 006			
Acid Number	mgKOH/g	30 -45	ML SC 001			
Softening Point (Ring and Ball)	°C	118 - 128	ML SC 002			
Viscosity Gardner-Holdt (25 °C)	-	D min.	ML SC 007			
Solubility	-	-	-			
* Acetates, Aliphatic Hydrocarbons, Aromatic Hydrocarbons	-	Soluble	ML SC 012			
* Alcohols	-	Insoluble	ML SC 012			

<sup>\*</sup> The sporadic analyzed parameters above do not characterize the product and should be taken only as reference.

## **APPLICATIONS**

- Paints and varnishes based on Nitrocellulose, synthetic enamel, flexographic paints, steam set;
- Paints for road marking.

## **BENEFITS**

- ✓ Promotes good hardness;
- ☑ Improves high gloss and fast drying

PACKAGING				
Туре	Size	Shelf life		
Flakes Paper bags	25 Kg	12 months		
DISCLAIMER				



To prevent accidents and environmental impacts, please check the product SDS. We request our customers to test our products before using them on industrial scale. The user of our products bears the responsibility of determining their suitability for a particular application or formulation or determining that the products or their use do not infringe any intellectual property.

We do not assume any responsibility or warranty, expressed or implied, resulting from handling, usage and storage whether performed according to the instructions contained in this document, whether used alone or in combination with other products.

The buyer assumes all responsibility and liability for loss or damage arising from the handling and use of our products, either alone or in combination with other products.

Elaborated: Allan Ribeiro / Jeferson Santos / Robson Chimin / Vitor Salvador	Revised: Joyce Custódio / Rafaela Silva	Approved: Vitor Salvador
--	--	--------------------------