

	TECHNICAL DATA SHEET	TDS 045		
		Revision:	Date:	Page:
		06	2024-07-02	1/1

RESIDHERE EP 120

Gum rosin modified with pentaerythritol and fumaric acid.

VERIFICATIONS			
Characteristics	UN	Specification / Tolerance	Method
Color Gardner	-	7 max.	ML SC 006
Acid Number	mgKOH/g	100 – 120	ML SC 001
Softening Point (Ring and Ball)	°C	110 – 120	ML SC 002
Solubility	-	-	-
* Acetates, Aromatic Hydrocarbons, Drying oil	-	Soluble	ML SC 012
* Alcohols	-	Insoluble	ML SC 012
* Aliphatic hydrocarbons	-	Insoluble	ML SC 012

* The sporadic analyzed parameters above do not characterize the product and should be taken only as reference.

APPLICATIONS

- Glues and adhesives in general;
- Additive agent for floors and mortar.

BENEFITS

- Thermal resistance.

PACKAGING

Type	Size	Shelf life
Paper bag (Flakes)	25 Kg	12 months

DISCLAIMER



To prevent accidents and environmental impacts, please check the product SDS. We request our customers to test our products before using them on industrial scale. Due to the thermoplastic behavior, pastillated and flaked resins may fuse, block or lump. This can be accelerated under any of the following conditions:

- 1) above 25°C temperature
- 2) prolonged storage
- 3) pressure, e.g., stacking pallets, or a combination of these conditions.

This is particularly applicable for low softening point resin grades. In order to maintain the flake or pastille shape, we therefore recommend storing the material in a temperature-controlled area; be careful with stacking material or applying pressure and preventing prolonged storage. It should be noted that lumping does not have a negative impact on the product specifications. Due to the nature of the product, claims regarding lumping cannot be accepted. Resins are prone to gradual oxidation, some more so than others.

This could result in darkening and/or it could have an adverse effect on the solubility of the resin in organic solvents or on its compatibility with polymers. Accordingly, it is recommended that strict control of inventory be observed at all times, taking care that the oldest material is used first. The user of our products bears the responsibility of determining their suitability for a particular application or formulation or determining that the products or their use do not infringe any intellectual property.

We do not assume any responsibility or warranty, expressed or implied, resulting from handling, usage and storage whether performed according to the instructions contained in this document, whether used alone or in combination with other products. The buyer assumes all responsibility and liability for loss or damage arising from the handling and use of our products, either alone or in combination with other products.

Elaborated: Allan Ribeiro / Jeferson Santos / Robson Chimin / Vitor Salvador	Revised: Joyce Custódio / Rafaela Silva	Approved: Vitor Salvador
---	---	---------------------------------

FSGI - 062 REV 03