

TECHNICAL DATA SHEET

T	DS	055	

Revision:	Date:	Page:
10	2024-06-24	1/1

RESIDHERE AB 115

Gum rosin modified with fumaric acid.

VERIFICATIONS						
Characteristics	UN	Specification / Tolerance	Method			
Color Gardner	-	12 max.	ML SC 006			
Acid Number	mgKOH/g	210 – 250	ML SC 001			
Softening Point (Ring and Ball)	°C	105 – 115	ML SC 002			
* Solubility	-	-	-			
* Acetates, Alcohols, Aromatic Hydrocarbons	-	Soluble	ML SC 012			

^{*} The sporadic analyzed parameters above do not characterize the product and should be taken only as reference.

APPLICATIONS

☑ Size for paper, raw material for resins

BENEFITS

Excellent tack.

PACKAGING					
Туре	Size	Shelf life			
Flakes paper bag	25 Kg	12 months			
Flakes big bag	500 Kg	12 months			

DISCLAIMER

To prevent accidents and environmental impacts, please check the product SDS. We request our customers to test our products before using them on industrial scale. The user of our products bears the responsibility of determining their suitability for a particular application or formulation or determining that the products or their use do not infringe any intellectual property.

We do not assume any responsibility or warranty, expressed or implied, resulting from handling, usage and storage whether performed according to the instructions contained in this document, whether used alone or in combination with other products.

The buyer assumes all responsibility and liability for loss or damage arising from the handling and use of our products, either alone or in combination with other products.

Elaborated: Allan Ribeiro / Jeferson Santos / Robson Chimin / Vitor Salvador	Revised: Joyce Custódio / Rafaela Silva	Approved: Vitor Salvador
---	--	--------------------------