GrupoRB	

# **RESIDHERE** AF 150

Gum rosin modified with fumaric acid.

VERIFICATIONS				
Characteristics	UN	Specification / Tolerance	Method	
Color Gardner	-	10 max.	ML SC 006	
Acid Number	mg KOH/g	185 – 205	ML SC 001	
Viscosity Gardner-Holdt (25 °C)	-	D min.	ML SC 007	
Softening Point (Ring and Ball)	°C	145 – 160	ML SC 002	
Solubility	-	-	-	
<ul> <li>* Acetates, Alcohols, Aromatic</li> <li>Hydrocarbons, Ammonium</li> </ul>	-	Soluble	ML SC 012	
* Aliphatic Hydrocarbons	-	Insoluble	ML SC 012	

\* The sporadic analyzed parameters above do not characterize the product and should be taken only as reference.

## APPLICATIONS

☑ Coating of fruits, paints and varnishes based on Nitrocellulose;

Synthetic enamel, flexographic paints and paints for road demarcation.

## BENEFITS

- ☑ Promotes high gloss, fast drying and good hardness;
- ☑ Soluble in aqueous ammonia and amines.

PACKAGING					
Туре	Size	Shelf life			
Flakes Plastic bags	25 Kg	12 months			
Flakes Paper bags	25 Kg	12 months			

## DISCLAIMER

To prevent accidents and environmental impacts, please check the product SDS.

## Allergens: Contains soy derivatives.

We request our customers to test our products before using them on industrial scale. The user of our products bears the responsibility of determining their suitability for a particular application or formulation or determining that the products or their use do not infringe any intellectual property.

We do not assume any responsibility or warranty, expressed or implied, resulting from handling, usage and storage whether performed according to the instructions contained in this document, whether used alone or in combination with other products. The buyer assumes all responsibility and liability for loss or damage arising from the handling and use of our products, either alone or in combination with other products.

Elaborated: Allan Ribeiro / Jeferson Santos / Robson Chimin / Vitor Salvador	<b>Revised:</b> Joyce Custódio / Rafaela Silva	Approved: Vitor Salvador
FSGI 062 REV 03		