RESIDHERE® DV 115 SM

MODIFIED ROSIN RESIN SPECIALLY DEVELOPED FOR ROAD MARKING.

RESIDHERE® DV 115 SM IS IDEAL FOR ROAD MARKINGS, PAINTS, AND VARNISHES IN GENERAL. IT PROMOTES HIGH GLOSS, QUICK DRYING, AND INCREASES ADHESION.

PROPERTIES.

Analysis	UN	Specification	Typical Values	Method
COLOR GARDNER	-	Max. 7	4.5	ML SCDV 006
ACID NUMBER	mg KOH/g	20- 30	24.5	ML SCDV 001
SOFTENING POINT	°C	110- 120	112	ML SCDV 002

PACKAGING

Type	Size	Shelf life
KRAFT PAPER BAG (FLAKES)	25 Kg	12 months
KRAFT PAPER BAG (PELLETS)	25 Kg	12 months

DISCLAIMER

To prevent accidents and impacts on the environment, consult the product's SDS. We ask our customers to test our products before using them on an industrial scale. Due to the Their thermoplastic behavior, resins in the form of pellets and scales can fuse, block or form lumps.

This behavior can be accelerated if subjected to one of the following conditions: Storage: 1) Temperatures above 25°C; 2) Extended storage; 3) pressure, for example, pallet stacking; or a combination of these conditions. This is particularly applicable for resin grades low softening point. To maintain the shape of scales or pellets, we recommend storing the material in temperature-controlled location; carefully when stacking the material and avoid prolonged storage. It should be note that blocking has no negative impact on product specifications. Due to the nature of the product, it is not Complaints about blocking will be accepted. Resins are subject to gradual oxidation, some more than others. This may result in darkening and/or may have an adverse effect on the solubility of the resin in organic solvents or in its compatibility with polymers. It is recommended that strict stock control be observed in all moments, taking care that the oldest material is used first. We assume no responsibility or warranties, express or implied, arising from improper handling, use, and storage. We do not We are responsible for products revalidated after the expiration date

This document is the property of RB Group. Reproduction prohibited.